



## PRODUCT SPECIFICATION SHEET

### Activated Carbon Powder

#### Product Specifications

Test	Specification	Typical Results
Apparent Density	ASTM D-2854	0.50 – 0.60 g/cc
Iodine	ASTM D-4607	>900 mg/g
Surface Area	N2 B.E.T Method	900 – 950 m2/g
Moisture as Packed	ASTM D-2867	2%
U.S. Standard Sieve Size: Larger than No.325, Max. (ASTM D-2862)	As reported	10%
U.S. Standard Sieve Size: Smaller than No.325, Max. (ASTM D-2862)	As reported	90%

Appropriate/legal use of this product is the responsibility of the user.

[Activated Carbon \(Charcoal\) Powder, Food Grade, Kosher, Halal, Wood Based](#)

Phone: 512-668-9918, Fax: 512-886-4008, E-mail: [customercare@laballey.com](mailto:customercare@laballey.com)  
[www.laballey.com](http://www.laballey.com)

12501 Pauls Valley Road, Suite A, Austin, Texas 78737  
© 2025 Lab Alley