

## PRODUCT SPECIFICATION SHEET

## Magnesium silicate

## Activated Magnesium Silicate, Lab Grade

Test	Specification	Typical Results
SiO <sub>2</sub>	62% ~ 68%	62.5%
MgO	13%~ 17%	13.4%
Appearance	White powder with good fluidity	Pass
PH value	9.5 ~10.5	9.7
Loss on drying	≤10%	4.3%
Particle size (250um to 150um)	≥90%	90.3%

Appropriate/legal use of this product is the responsibility of the user